

# PATENT COOPERATION TREATY

## PCT

LIST OF DOCUMENTS FILED WITH THE  
INTERNATIONAL BUREAU  
AS RECEIVING OFFICE

To:

The International Bureau of WIPO  
PCT Receiving Office Section  
34, chemin des Colombettes  
1211 Geneva 20  
Switzerland

Facsimile No. +41 22 910 06 10

Applicant's or agent's file reference

1085-024WO01

International application No.  
(if known)

International filing date (day/month/year)  
(if known)

(Earliest) Priority date  
(day/month/year)

10 December 2004 (10.12.2004)

Applicant

NISSAN MOTOR CO., LTD. et al.

Title of invention

CUTTING TOOLS AND ROUGHENED ARTICLES USING SURFACE  
ROUGHENING METHODS

The applicant hereby requests the International Bureau to acknowledge to the following person (include full name, address, facsimile No. and telephone No.):

Kent J. Sieffert  
Shumaker & Sieffert, P.A.  
8425 Seasons Parkway, Suite 105  
St. Paul, Minnesota  
United States of America

Telephone: 651-735-1100

Facsimile: 651-735-1102

the receipt by the following means:

☐ mail (surface, air mail, registered)    ☐ delivery service    ☒ facsimile transmission    ☐ hand delivery

of the documents/elements listed below:

- ☒ PCT request (including declaration sheets) ( 4 pages)
- ☒ description (excluding sequence listing and/or tables relating thereto) ( 14 pages)
- ☒ claims ( 6 pages)
- ☒ abstract ( 1 pages)
- ☒ drawings ( 7 pages)
- ☐ sequence listing and/or tables relating thereto ( pages)
- ☒ fee calculation sheet
- ☐ separate authorization to charge deposit account
- ☒ cheque (indicate currency and amount) \$3082.00 (U.S. Dollars)
- ☐ cash (in person only) (indicate amount)
- ☐ power of attorney (general power, copy of general power, separate power) (indicate kind and number)
- ☐ statement explaining lack of signature (if more than one, indicate number)
- ☒ priority document (if more than one, indicate number)
- ☐ separate indications concerning deposited microorganism or other biological material ( pages)
- ☐ sequence listing and/or tables relating thereto in electronic form (indicate type and number of carriers)
- ☐ statement accompanying sequence listing and/or tables relating thereto in electronic form (if more than one, indicate number)
- ☐ accompanying letter
- ☐ other (specify):

# PCT

## REQUEST

The undersigned requests that the present international application be processed according to the Patent Cooperation Treaty.

For receiving Office use only

International Application No.

International Filing Date

Name of receiving Office and "PCT International Application"

Applicant's or agent's file reference  
(if desired) (12 characters maximum) 1085-024WO01

<b>Box No. I TITLE OF INVENTION</b> CUTTING TOOLS AND ROUGHENED ARTICLES USING SURFACE ROUGHENING METHODS	
<b>Box No. II APPLICANT</b> <input type="checkbox"/> This person is also inventor	
Name and address: (Family name followed by given name; for a legal entity, full official designation. The address must include postal code and name of country. The country of the address indicated in this Box is the applicant's State (that is, country) of residence if no State of residence is indicated below.) NISSAN MOTOR CO., LTD. 2 Takara-cho, Kanagawa-ku Yokohama-shi, Kanagawa 221-0023 Japan	
Telephone No.	
Facsimile No.	
Teleprinter No.	
Applicant's registration No. with the Office	
State (that is, country) of nationality: Japan	State (that is, country) of residence: Japan
This person is applicant for the purposes of: <input type="checkbox"/> all designated States <input checked="" type="checkbox"/> all designated States except the United States of America <input type="checkbox"/> the United States of America only <input type="checkbox"/> the States indicated in the Supplemental Box	
<b>Box No. III FURTHER APPLICANT(S) AND/OR (FURTHER) INVENTOR(S)</b>	
Name and address: (Family name followed by given name; for a legal entity, full official designation. The address must include postal code and name of country. The country of the address indicated in this Box is the applicant's State (that is, country) of residence if no State of residence is indicated below.) NISSAN NORTH AMERICA 990 West 190th Street Torrance, California 90502 United States of America	
This person is: <input checked="" type="checkbox"/> applicant only <input type="checkbox"/> applicant and inventor <input type="checkbox"/> inventor only (If this check-box is marked, do not fill in below.)	
Applicant's registration No. with the Office	
State (that is, country) of nationality: U.S.	State (that is, country) of residence: U.S.
This person is applicant for the purposes of: <input type="checkbox"/> all designated States <input checked="" type="checkbox"/> all designated States except the United States of America <input type="checkbox"/> the United States of America only <input type="checkbox"/> the States indicated in the Supplemental Box	
<input checked="" type="checkbox"/> Further applicants and/or (further) inventors are indicated on a continuation sheet.	
<b>Box No. IV AGENT OR COMMON REPRESENTATIVE; OR ADDRESS FOR CORRESPONDENCE</b>	
The person identified below is hereby/has been appointed to act on behalf of the applicant(s) before the competent International Authorities as: <input checked="" type="checkbox"/> agent <input type="checkbox"/> common representative	
Name and address: (Family name followed by given name; for a legal entity, full official designation. The address must include postal code and name of country.) SIEFFERT, Kent J. Shumaker & Sieffert, P.A. 8425 Seasons Parkway, Suite 105 St. Paul, Minnesota 55125 United States of America	
Telephone No. 651-735-1100	
Facsimile No. 651-735-1102	
Teleprinter No.	
Agent's registration No. with the Office 41,312	
<input type="checkbox"/> Address for correspondence: Mark this check-box where no agent or common representative is/has been appointed and the space above is used instead to indicate a special address to which correspondence should be sent.	

## Continuation of Box No. III FURTHER APPLICANT(S) AND/OR (FURTHER) INVENTOR(S)

If none of the following sub-boxes is used, this sheet should not be included in the request.

Name and address: (Family name followed by given name; for a legal entity, full official designation. The address must include postal code and name of country. The country of the address indicated in this Box is the applicant's State (that is, country) of residence if no State of residence is indicated below.)

IIZUMI, Masahiko  
1211-7 Daigiri  
Fujisawa-shi, Kanagawa 251-0002  
Japan

This person is:

- ☐ applicant only  
☒ applicant and inventor  
☐ inventor only (If this check-box is marked, do not fill in below.)

Applicant's registration No. with the Office

State (that is, country) of nationality:

Japan

State (that is, country) of residence:

Japan

This person is applicant for the purposes of:

☐ all designated States

☐ all designated States except the United States of America

☒ the United States of America only

☐ the States indicated in the Supplemental Box

Name and address: (Family name followed by given name; for a legal entity, full official designation. The address must include postal code and name of country. The country of the address indicated in this Box is the applicant's State (that is, country) of residence if no State of residence is indicated below.)

NISHIMURA, Kimio  
16-49 Ninomaru, Tsuzuki-ku  
Yokohama-shi, Kanagawa 224-0052

This person is:

- ☐ applicant only  
☒ applicant and inventor  
☐ inventor only (If this check-box is marked, do not fill in below.)

Applicant's registration No. with the Office

State (that is, country) of nationality:

Japan

State (that is, country) of residence:

Japan

This person is applicant for the purposes of:

☐ all designated States

☐ all designated States except the United States of America

☒ the United States of America only

☐ the States indicated in the Supplemental Box

Name and address: (Family name followed by given name; for a legal entity, full official designation. The address must include postal code and name of country. The country of the address indicated in this Box is the applicant's State (that is, country) of residence if no State of residence is indicated below.)

This person is:

- ☐ applicant only  
☐ applicant and inventor  
☐ inventor only (If this check-box is marked, do not fill in below.)

Applicant's registration No. with the Office

State (that is, country) of nationality:

State (that is, country) of residence:

This person is applicant for the purposes of:

☐ all designated States

☐ all designated States except the United States of America

☐ the United States of America only

☐ the States indicated in the Supplemental Box

Name and address: (Family name followed by given name; for a legal entity, full official designation. The address must include postal code and name of country. The country of the address indicated in this Box is the applicant's State (that is, country) of residence if no State of residence is indicated below.)

This person is:

- ☐ applicant only  
☐ applicant and inventor  
☐ inventor only (If this check-box is marked, do not fill in below.)

Applicant's registration No. with the Office

State (that is, country) of nationality:

State (that is, country) of residence:

This person is applicant for the purposes of:

☐ all designated States

☐ all designated States except the United States of America

☐ the United States of America only

☐ the States indicated in the Supplemental Box

☐ Further applicants and/or (further) inventors are indicated on another continuation sheet.

**Box No. V DESIGNATIONS**

The filing of this request constitutes under Rule 4.9(a), the designation of all Contracting States bound by the PCT on the international filing date, for the grant of every kind of protection available and, where applicable, for the grant of both regional and national patents.

However,

- ☐ DE Germany is not designated for any kind of national protection
- ☐ KR Republic of Korea is not designated for any kind of national protection
- ☐ RU Russian Federation is not designated for any kind of national protection

*(The check-boxes above may be used to exclude (irrevocably) the designations concerned in order to avoid the ceasing of the effect, under the national law, of an earlier national application from which priority is claimed. See the Notes to Box No. V as to the consequences of such national law provisions in these and certain other States.)*

**Box No. VI PRIORITY CLAIM**

The priority of the following earlier application(s) is hereby claimed:

Filing date of earlier application (day/month/year)	Number of earlier application	Where earlier application is:		
		national application: country or Member of WTO	regional application:* regional Office	international application: receiving Office
item (1) 10 December 2004 (10.12.2004)	2004-358712	JP		
item (2)				
item (3)				

☐ Further priority claims are indicated in the Supplemental Box.

The receiving Office is requested to prepare and transmit to the International Bureau a certified copy of the earlier application(s) (only if the earlier application was filed with the Office which for the purposes of this international application is the receiving Office) identified above as:

☒ all items    ☐ item (1)    ☐ item (2)    ☐ item (3)    ☐ other, see Supplemental Box

\* Where the earlier application is an ARIPO application, indicate at least one country party to the Paris Convention for the Protection of Industrial Property or one Member of the World Trade Organization for which that earlier application was filed (Rule 4.10(b)(ii)):

**Box No. VII INTERNATIONAL SEARCHING AUTHORITY**

Choice of International Searching Authority (ISA) (if two or more International Searching Authorities are competent to carry out the international search, indicate the Authority chosen; the two-letter code may be used):

ISA / .EP.....

Request to use results of earlier search; reference to that search (if an earlier search has been carried out by or requested from the International Searching Authority):

Date (day/month/year)

Number

Country (or regional Office)

**Box No. VIII DECLARATIONS**

The following declarations are contained in Boxes Nos. VIII (i) to (v) (mark the applicable check-boxes below and indicate in the right column the number of each type of declaration):

Number of  
declarations

- |   |  |   |
|---|--|---|
| <input type="checkbox"/> Box No. VIII (i)   | Declaration as to the identity of the inventor   | : |
| <input type="checkbox"/> Box No. VIII (ii)  | Declaration as to the applicant's entitlement, as at the international filing date, to apply for and be granted a patent             | : |
| <input type="checkbox"/> Box No. VIII (iii) | Declaration as to the applicant's entitlement, as at the international filing date, to claim the priority of the earlier application | : |
| <input type="checkbox"/> Box No. VIII (iv)  | Declaration of inventorship (only for the purposes of the designation of the United States of America)                               | : |
| <input type="checkbox"/> Box No. VIII (v)   | Declaration as to non-prejudicial disclosures or exceptions to lack of novelty   | : |

**Box No. IX CHECK LIST; LANGUAGE OF FILING**

This international application contains: (a) on paper, the following number of sheets:	This international application is accompanied by the following item(s) (mark the applicable check-boxes below and indicate in right column the number of each item):	Number of items
request (including declaration sheets) : 4	1. <input checked="" type="checkbox"/> fee calculation sheet	1
description (excluding sequence listing and/or tables related thereto) : 14	2. <input type="checkbox"/> original separate power of attorney	
claims : 6	3. <input type="checkbox"/> original general power of attorney	
abstract : 1	4. <input type="checkbox"/> copy of general power of attorney; reference number, if any: .....	
drawings : 7	5. <input type="checkbox"/> statement explaining lack of signature	
<b>Sub-total number of sheets</b> : 32	6. <input checked="" type="checkbox"/> priority document(s) identified in Box No. VI as item(s): .....	1
sequence listing : .....	7. <input type="checkbox"/> translation of international application into (language): .....	
tables related thereto : .....	8. <input type="checkbox"/> separate indications concerning deposited microorganism or other biological material	
(for both, actual number of sheets if filed on paper, whether or not also filed in electronic form; see (c) below)	9. <input type="checkbox"/> sequence listing in electronic form (indicate type and number of carriers)	
<b>Total number of sheets</b> : 32	(i) <input type="checkbox"/> copy submitted for the purposes of international search under Rule 13ter only (and not as part of the international application):	
(b) <input type="checkbox"/> only in electronic form (Section 801(a)(i))	(ii) <input type="checkbox"/> (only where check-box (b)(i) or (c)(i) is marked in left column) additional copies including, where applicable, the copy for the purposes of international search under Rule 13ter	
(i) <input type="checkbox"/> sequence listing	(iii) <input type="checkbox"/> together with relevant statement as to the identity of the copy or copies with the sequence listing mentioned in left column	
(ii) <input type="checkbox"/> tables related thereto	10. <input type="checkbox"/> tables in electronic form related to sequence listing (indicate type and number of carriers)	
(c) <input type="checkbox"/> also in electronic form (Section 801(a)(ii))	(i) <input type="checkbox"/> copy submitted for the purposes of international search under Section 802(b-quater) only (and not as part of the international application)	
(i) <input type="checkbox"/> sequence listing	(ii) <input type="checkbox"/> (only where check-box (b)(ii) or (c)(ii) is marked in left column) additional copies including, where applicable, the copy for the purposes of international search under Section 802(b-quater)	
(ii) <input type="checkbox"/> tables related thereto	(iii) <input type="checkbox"/> together with relevant statement as to the identity of the copy or copies with the tables mentioned in left column	
Type and number of carriers (diskette, CD-ROM, CD-R or other) on which are contained the	11. <input checked="" type="checkbox"/> other (specify): P.C.T./RO/198 (RO/IB)	1
<input type="checkbox"/> sequence listing: .....		
<input type="checkbox"/> tables related thereto: .....		
(additional copies to be indicated under items 9(ii) and/or 10(ii), in right column)		

Figure of the drawings which should accompany the abstract: 7

Language of filing of the international application: English

**Box No. X SIGNATURE OF APPLICANT, AGENT OR COMMON REPRESENTATIVE**

Next to each signature, indicate the name of the person signing and the capacity in which the person signs (if such capacity is not obvious from reading the request).

Kent J. Sieffert  
 Kent J. Sieffert  
 Agent for Applicant

For receiving Office use only		2. Drawings: <input type="checkbox"/> received:  <input type="checkbox"/> not received:
1. Date of actual receipt of the purported international application:		
3. Corrected date of actual receipt due to later but timely received papers or drawings completing the purported international application:		
4. Date of timely receipt of the required corrections under PCT Article 11(2):		
5. International Searching Authority (if two or more are competent): ISA /	6. <input type="checkbox"/> Transmittal of search copy delayed until search fee is paid	

For International Bureau use only
Date of receipt of the record copy by the International Bureau:

This sheet is not part of and does not count as a sheet of the international application.

PCT

FEE CALCULATION SHEET

Annex to the Request

For receiving Office use only

International Application No.

Applicant's or agent's  
file reference

1085-024WO01

Date stamp of the receiving Office

Applicant

NISSAN MOTOR CO., LTD.

CALCULATION OF PRESCRIBED FEES

1. TRANSMITTAL FEE . . . . . 79.00 [T]

2. SEARCH FEE . . . . . 1877.00 [S]

International search to be carried out by EP  
(If two or more International Searching Authorities are competent to carry out the international search, indicate the name of the Authority which is chosen to carry out the international search.)

3. INTERNATIONAL FILING FEE

Where items (b) and/or (c) of Box No. IX apply, enter Sub-total number of sheets } 32  
Where items (b) and (c) of Box No. IX do not apply, enter Total number of sheets }

[i1] first 30 sheets . . . . . 1102.00 [i1]

[i2] 2 x 12 = 24.00 [i2]  
number of sheets fee per sheet  
in excess of 30

[i3] additional component (only if a sequence listing and/or tables  
related thereto are filed in electronic form under Section 801(a)(i),  
or both in that form and on paper, under Section 801(a)(ii):

400 x                      = 0.00 [i3]  
fee per sheet

Add amounts entered at i1, i2 and i3 and enter total at I . . . . . 1126.00 [I]

(Applicants from certain States are entitled to a reduction of 75% of the international filing fee. Where the applicant is (or all applicants are) so entitled, the total to be entered at I is 25% of the international filing fee.)

4. FEE FOR PRIORITY DOCUMENT (if applicable) . . . . . 0.00 [P]

5. TOTAL FEES PAYABLE . . . . . 3082.00

Add amounts entered at T, S, I and P, and enter total in the TOTAL box

TOTAL

MODE OF PAYMENT (Not all modes of payment may be available at all receiving Offices)

- ☐ authorization to charge deposit account (see below) ☐ postal money order ☐ cash ☐ coupons  
☒ cheque ☐ bank draft ☐ revenue stamps ☐ other (specify):

AUTHORIZATION TO CHARGE (OR CREDIT) DEPOSIT ACCOUNT

(This mode of payment may not be available at all receiving Offices)

- ☐ Authorization to charge the total fees indicated above.  
☐ (This check-box may be marked only if the conditions for deposit accounts of the receiving Office so permit) Authorization to charge any deficiency or credit any overpayment in the total fees indicated above.  
☐ Authorization to charge the fee for priority document.

Receiving Office: RO/

Deposit Account No.:

Date:

Name:

Signature:

10/572726

日本国特許庁  
JAPAN PATENT OFFICE

AP20 Rec'd PCT/PTO 21 MAR 2006

別紙添付の書類に記載されている事項は下記の出願書類に記載されて  
いる事項と同一であることを証明する。

This is to certify that the annexed is a true copy of the following application as filed  
with this Office.

出願年月日  
Date of Application: 2004年12月10日

出願番号  
Application Number: 特願2004-358712

パリ条約による外国への出願  
用いる優先権の主張の基礎  
となる出願の国コードと出願  
番号  
the country code and number  
of your priority application,  
as used for filing abroad  
under the Paris Convention, is


J P 2 0 0 4 - 3 5 8 7 1 2

願人  
Applicant(s): 日産自動車株式会社

2005年 7月25日

特許庁長官  
Commissioner,  
Japan Patent Office

小川



**CUTTING TOOLS AND ROUGHENED ARTICLES**  
**USING SURFACE ROUGHENING METHODS**

[0001] This application claims priority from Japanese Patent Application No. 2004-358712, filed December 10, 2004, the entire contents of which is incorporated herein by reference.

**TECHNICAL FIELD**

[0002] The invention relates to methods of surface roughening and cutting tools useful in surface roughening, as well as articles having roughened surfaces, particularly articles useful in manufacturing internal combustion engines for motor vehicle applications.

**BACKGROUND**

[0003] Internal combustion engines are increasingly fabricated using lightweight metals such as aluminum to decrease weight and achieve greater fuel efficiency. In particular, aluminum cylinder blocks have recently been fabricated with the internal surfaces of the cylinder bores spray coated with a material which acts to lubricate the cylinder bore and which aids the disposal of the engine's exhaust gases, for example, by catalyzing chemical reactions associated with the combustion process.

[0004] When the inner surface of a cylinder bore of a liner-less aluminum cylinder block is spray-coated, it is generally necessary to roughen the inner surface of the cylinder bore beforehand to enhance the adhesion of the spray coating. Surface roughening may be achieved, for example, using bead blasting, high pressure water jet blasting, or mechanical machining methods. However, these methods may not lead to a uniformly roughened surface, which can lead to adhesion failure of the coating to the cylinder wall. In addition, conventional machining methods can be time intensive and expensive, often requiring multiple pass machining steps to produce a cylinder bore surface having sufficient roughness to adhere the thermally sprayed coating.

[0005] Thus, a more reproducible and cost effective surface roughening method has been sought. The art continually searches for new methods of surface roughening, particularly roughening of cylindrical metal surfaces useful in fabricating internal combustion engines.



## SUMMARY

**[0006]** In general, the disclosure relates to methods of surface roughening, cutting tools useful in practicing the surface roughening methods, and articles having surfaces roughened using the methods. More particularly, the disclosure relates to mechanical surface roughening methods useful for metal surfaces, more specifically, cylindrical metal surfaces. The surface roughening methods, cutting tools and articles, may be useful in manufacturing internal combustion engines for motor vehicle applications.

**[0007]** In one embodiment, the method includes forming a pattern of peaks and valleys on a surface of an article in a longitudinal axial direction with a leading edge of a rotary cutting head having the leading edge and a trailing edge, applying a stress to the peaks with the trailing edge of the cutting head, and fracturing the peaks to create a fracture surface defining lands separating the valleys defining grooves. In certain embodiments, each groove is symmetrical. In some embodiments, each groove defines a v-shape.

**[0008]** In additional embodiments, the method includes applying a coating to the roughened surface. In certain embodiments, the coating is applied using at least one of chemical vapor deposition, plasma deposition, thermal spray coating, and fluid spray coating. The coating may include an abrasion resistant material. In some embodiments, the coating includes a ceramic material or a metal.

**[0009]** In one exemplary embodiment, the method includes feeding a cutting tool comprising a cutting head further comprising a radial cutting blade with first and second cutting edges along a longitudinal axis of an article while rotating the cutting head about the axis. The first cutting edge forms a first machined pattern of peaks and valleys on a surface of the article, and the second cutting edge removes at least a portion of the peaks to form roughened fracture surfaces in a second machined pattern defining an arrangement of grooves, corresponding to the valleys, separated by the roughened fracture surfaces.

**[0010]** In another embodiment, a cutting tool comprises a rotary cutting head including at least one cutting blade extending radially outward from a cutting head. The cutting blade has a body, a first planar surface defining a first cutting edge shaped to cut a first pattern of peaks and valleys into a surface, and a second planar surface defining a fracture surface formation blade shaped to fracture the peaks and thereby create lands separating the valleys forming grooves in a second pattern. The cutting head may include at least one of a metal, a ceramic, or diamond.

**[0011]** In some embodiments, the cutting edge applies stress to a cross-section of each peak in an axial direction along a longitudinal axis of a surface at a starting location, and the fracture surface formation blade fractures each peak beginning at the starting location. In certain embodiments, the fracture surface formation blade fractures the entire cross section of each peak in the axial direction by applying the stress to the entire peak in a non-axial direction. In additional embodiments, the fracture surface formation blade includes an irregularly shaped part having a plurality of fracture surface formation blade projections and depressions adapted to form an irregularly shaped fracture surface defining a land including a plurality of fracture surface projections and depressions formed by fracturing the entire cross section of each peak. In exemplary embodiments, the lands are additionally roughened by the trailing edge of the cutting head.

**[0012]** In another embodiment, a surface roughening system comprises a means for roughening a surface further comprising a first cutting edge means for cutting a first pattern of peaks and valleys into the surface. The means for roughening further comprises a second cutting edge means for fracturing the peaks, a means for moving the means for roughening in an axial direction relative to a longitudinal axis of the surface, and a means for rotating the means for roughening in a radial direction relative to the surface. According to certain embodiments of this surface roughening system, rotating the means for roughening while feeding the means for roughening relative to the surface creates a roughened surface comprising a second pattern, wherein the second pattern includes a plurality of lands created by fracturing the peaks, each land positioned adjacent to a groove corresponding to a valley in the first pattern.

**[0013]** In yet another embodiment, a cylindrical body comprises a machine roughened surface including a substantially helical pattern of grooves separated by substantially uniform roughened surface regions defining lands. In some embodiments, the cross section of the grooves is substantially symmetrical and has a v-shape. In certain embodiments, the roughened surface is an interior surface of the cylindrical body. In some embodiments, the cylindrical body may be formed from a nonferrous metal. In additional embodiments, a coating is applied to the surface overlaying the lands and grooves.

**[0014]** In certain embodiments, the cylindrical body is a cylinder block for an internal combustion engine. In exemplary embodiments, the article includes at least one cylinder liner positioned in the cylinder bore of the engine. The cylinder liner may include an

outer peripheral surface roughened by forming thereon the pattern of lands and grooves, before casting the cylinder liner into a cylinder bore of an internal combustion engine.

[0015] The details of one or more embodiments of the invention are set forth in the accompanying drawings and the description below. Other features, objects, and advantages of the invention will be apparent from the description and drawings, and from the claims.

### **BRIEF DESCRIPTION OF DRAWINGS**

[0016] FIG. 1 is a cross-sectional view of a cylinder block showing a surface roughening method.

[0017] FIG. 2 is a front view of an exemplary cutting tool useful in practicing the surface roughening method of FIG. 1.

[0018] FIG. 3 is a side view of the cutting tool of FIG. 2.

[0019] FIG. 4 is a bottom view of the cutting tool of FIG. 2.

[0020] FIG. 5 is an enlarged perspective view of the cutting head of the exemplary cutting tool of FIG. 2.

[0021] FIG. 5A is an enlarged perspective view of the cutting edges on the cutting head of the exemplary cutting tool of FIG. 2.

[0022] FIG. 6 is an overhead view in perspective of the cutting head of FIG. 5.

[0023] FIG. 7 is an enlarged cross-sectional view showing a state of cutting with a cutting blade that is part of the cutting head of FIG. 5.

[0024] FIG. 8 is a front view of a cutting tool showing another exemplary embodiment of a cutting head.

[0025] FIG. 9 is a cross-sectional view showing an enlargement of a part D in FIG. 8.

[0026] FIG. 10 is an enlarged cross-sectional view showing the state of cutting with a cutting blade that is part of the cutting head of FIG. 8.

[0027] FIG. 11 is a cross-sectional view showing the state of cutting with a cutting head that includes an irregularly shaped fracture surface formation blade that additionally roughens a fracture surface.

[0028] FIG. 12 is a block diagram showing an outline of exemplary thermal spraying equipment useful in forming a thermal spray coating on a cylinder bore inner surface that is roughened.

[0029] FIG. 13 is a cross-sectional view of an exemplary surface roughened cylinder block (e.g. made of an aluminum alloy) for an internal combustion engine in which a cylinder liner (e.g. made of cast iron) is integrally molded.

[0030] FIG. 14A is an overhead view of the cylinder liner in FIG. 13.

[0031] FIG. 14B is a perspective view of FIG. 14A showing the roughened exterior peripheral surface of the cylinder liner of FIG. 13.

[0032] FIG. 15 is an exploded perspective view of exemplary casting molds used to cast and form a cylinder block for an internal combustion engine as shown in FIG. 13.

### DETAILED DESCRIPTION

[0033] The present invention is generally related to a surface roughening method in which a cutting tool is moved along a longitudinal axis of a body. As the cutting tool rotates about the longitudinal axis of the body, a first cutting edge extending radially outward a first distance from a cutting head of the cutting tool moves relative to the body and cuts on a surface of the body a first machined pattern of peaks and valleys. A second cutting edge extending radially outward a second distance from the cutting head of the cutting tool applies stress on the peaks in the first pattern, which fractures the peaks to create fractured surfaces and form a second machined pattern in the on the surface of the body. In the second machined pattern the fractured surfaces are lands separated by grooves, which correspond to the valleys remaining from the first machined pattern. By fracturing the peaks using the second cutting edge of the cutting tool, the lands of the second machined pattern are more uniform and symmetrical compared to machining techniques in which the fracture surface is formed by cutting chips generated as the machining proceeds.

[0034] The surface roughening method according to some embodiments of the present invention may thus lead to more uniformly shaped surface roughness patterns, which increases the adhesion strength and uniformity of a thermal spray coating applied to the roughened surface. The roughened surface may be used in, for example, an internal surface of a cylinder bore of an internal combustion engine. In additional embodiments, the adhesion strength between two articles may also be increased using the surface roughening method to roughen an external peripheral surface of, for example, a cylinder liner that is to be inserted as a sleeve into a cast cylinder block.

[0035] Various exemplary embodiments of the present invention will now be described with reference to the drawings. By specifying particular steps in the present disclosure, it

is not meant to limit the invention to performing those steps in a particular order unless an order is specified. Similarly, listing particular steps in a particular order is not intended to preclude intermediate steps or additional steps, as long as the enumerated steps appear in the order as specified. Certain materials and articles suitable for practicing the present invention are disclosed; however, additional equivalent materials and articles may be substituted in practicing the invention, as known to one skilled in the art. The detailed description of the present invention is not intended to describe every embodiment or each implementation of the present invention. Other embodiments and their equivalents are within the scope of the present invention.

**[0036]** In the particular examples described below and in FIG. 1, the article to be surface roughened is a cylinder bore 3 of a cylinder block 1. The bore 3 has a cylindrical body, and a cylinder bore inner surface 5 that is to be roughened. However, the surface to be roughened need not be an inner surface, but may be an outer surface. The article to be roughened using the surface roughening methods described herein is not limited to a cylinder bore part, but may, for example, be a pipe, a cylindrical bearing surface (e.g. a boss within a tie rod or other bearing surface), a transmission, and the like. In addition, the article need not have a cylindrical shape.

**[0037]** The article may be formed using any number of methods; however, die-casting is a presently preferred method. The article may generally be formed from a metal, for example, a nonferrous metal alloy such as an aluminum alloy (e.g. ADC 12 manufactured by Nissan Motors Company, Tokyo, Japan). However, other machinable materials (e.g. rigid plastics and the like) may be used in practicing the invention according to some embodiments.

**[0038]** FIG. 1 is a cross-sectional view of a cylinder block 1 of an engine showing a surface roughening method, cutting tool and article according to various embodiments of the present invention. Once the cylinder bore inner surface 5 is roughened by means of the method described below, a coating material may be applied to the roughened cylinder bore inner surface 5 to form a coating. In some embodiments, the coating is applied using at least one of chemical vapor deposition, plasma deposition, thermal spray coating, and fluid spray coating. Preferably, the coating is applied using thermal spray coating. The coating may include an abrasion resistant material. In some embodiments, the coating includes a ceramic material or a metal. Preferably, the thermal spray coating material includes a ferrous metal.

[0039] As shown in FIG. 2, a cutting tool including a boring bar 9 terminating at a radial cutting head 7 may be used to roughen the surface of the cylinder bore inner surface 5. FIG. 3 is a side view of the cutting tool of FIG. 2, and FIG. 4 is a bottom view of the cutting tool of FIG. 2. On the boring bar 9, a notch 13 that is used to form a concave surface is formed on the side of the tip of the lower part of a tool body 11 in FIG. 2, and the cutting head 7 is fixed by fastening with a bolt 15 at the end of the tool body 11 that protrudes from the notch 13. FIG. 5 is an enlarged perspective view of the cutting head 7 shown in the FIG. 2, and FIG. 6 is an overhead view of FIG. 5.

[0040] In one exemplary method of surface roughening, the cutting head 7 moves along the longitudinal axis A of the cylinder 3 (FIG. 1). The tool body 11 rotates about the longitudinal axis B (FIG. 1), and a single cutting blade 7a protrudes outward from a side face 11a of the tool body 11 to cut the surface 5 into a substantially helical thread-like pattern to roughen the surface. However, the surface roughening method may also be performed by holding the boring bar 9 may in a fixed state and moving the cylinder block 1 axially and rotationally.

[0041] As shown in FIGs. 5, 5A and 6, this exemplary cutting head 7 includes three cutting blades 7a extending radially outward from the body 8 of the cutting head at even angular intervals. In certain embodiments, each of the three cutting blades 7a can be removed when worn from cutting, and by attaching them on the tool body 11 again while rotating the cutting head body 8 120 degrees from the state in FIG. 4, another fresh cutting blade 7a can be used. It should be emphasized that the cutting head configuration shown in FIGs. 5, 5A and 6 is only exemplary, and many different cutting tool shapes may be used, as long as a first cutting edge of the cutting blade makes a pattern of peaks and a second cutting edge fractures the peaks to form fracture surfaces.

[0042] Referring to FIGs. 5, 5A and 6, each cutting blade 7a includes a first planar region 7b oriented at an obtuse angle  $\delta$  below a plane formed by the body 8 of the cutting head 7. The first planar region 8b extends radially outward a first distance  $d_1$  from a center 8b of the body 8 and intersects with a first rake face 7d to form a first cutting edge 7g. The angle  $\sigma$  between the first planar surface 7b and the first rake face 7d is selected to form a pattern of peaks and valleys in the surface to be cut. The angle  $\sigma$  is typically selected such that each machined valley in the surface 5 is symmetrical, and in a preferred embodiment each valley has a cross sectional v-shape. The first planar region 7b extends from the first rake face 7d at a leading edge of the cutting blade 7a, which is substantially normal to the planar region 7b, to a second rake face 7e at a trailing edge of the cutting

blade 7a, which is also substantially normal to the planar region 7b. A second planar region 7c is formed at an acute angle  $\theta$  above the first planar region 7b. The second planar region 7c extends radially outward a second distance  $d_2$  from the center 8b of the body 8 and intersects with the first rake face 7d to form a second cutting edge 7h. The second planar region 7c also extends from the first leading edge rake face 7d to the second trailing edge rake face 7e. The second planar region 7c is substantially normal to an end face 7f, which may optionally include a surface pattern.

**[0043]** In operation, the first cutting edge 7g cuts into the surface 5 of the cylindrical body a first machined pattern of peaks and valleys, and the first machined pattern will typically be a substantially helical thread-like pattern. The first cutting edge 7g preferably has an angle  $\sigma$  selected such that each machined valley in the surface 5 is symmetrical, and in a preferred embodiment each valley has a v-shape when viewed in cross section. The second cutting edge 7h then applies stress to the peaks of the first substantially helical pattern, which fractures the peaks and forms a second machined pattern in the surface 5. The second machined pattern is also typically a substantially helical thread-like pattern. In the second machined pattern the fractured peaks create fracture surfaces separated by grooves, which are the valleys remaining from the first machined pattern.

**[0044]** The cutting head 7 may be fabricated from any number of materials, but generally includes at least one of a metal, a ceramic material, or diamond. The cutting blades 7a generally include at least one metal selected from titanium, tungsten, cobalt, nickel, iron, or aluminum. The cutting edge 7a and in particular, the fracture surface formation second cutting edge 7h, may include at least one ceramic material selected from one or more of silicon nitride, silicon carbide, aluminum oxide, silicon dioxide, or titanium nitride. Preferably, the cutting blades 7a are harder than the surface of the material to be roughened.

**[0045]** In some embodiments, the disclosure provides a surface roughening system, including a means for roughening a surface (e.g. cutting head 7), further including a first cutting edge means (e.g. first cutting edge 7g) for cutting a pattern of peaks and valleys into the surface to form the first substantially helical pattern, and a second cutting edge means (e.g. fracture surface second cutting edge 7h) for fracturing the peaks to form the second substantially helical pattern including roughened lands interspersed with grooves; a means for feeding (not shown in FIG. 1); and a means for rotating (not shown in FIG. 1).

[0046] As shown in FIG. 7, which shows cutting using the cutting blade 7a in which the parts shown in FIGs. 5, 5A and 6 are enlarged, the first planar region 7c with the second cutting edge 7h applies stress on a peak 17 remaining from the first machined pattern formed by the first cutting edge 7g on the cylinder bore inner surface 5. The second cutting edge 7h removes a portion of the peak 17 and forms a fracture surface 19. A cutting chip 21 is generated by the cut with the cutting blade 7a, and the cutting head 7 is assumed to move out of the plane of the paper in FIG. 7 and vertically upward toward the viewer.

[0047] In the perspective of FIG. 7, the projecting part 7c and second cutting edge 7h of the cutting blade 7a apply stress beneath the peak 17 and the cutting blade 7a moved vertically upward toward the viewer and out of the paper to fracture the peak 17 and form a fracture surface 19. Using the above described cutting tool 7a make the peak 17 relatively easy to fracture in a uniform and consistent way, and the shape of the fracture surface 19 is more uniform and symmetrical compared to conventional processes in which the fracture surface is randomly formed by cutting chips produced by the first cutting edge of the cutting blade. In addition, since the peak 17 is easily fractured using the projecting part 7c, the cutting stress applied on the cutting blade 7a is reduced, which would be expected to extend the life of the cutting head 7. Preferably, as shown in FIG. 7, the entire cross section of each peak in the axial direction is fractured by applying the stress to each peak in a non-axial direction.

[0048] Since the shape of the fracture surface 19 is more uniform and symmetrical as described above, the coating applied to the surface 5 adheres more strongly and more uniformly, which enhances the durability of the coating.

[0049] FIG. 8 is a perspective view of a cutting head 70 corresponding to FIGs. 5, 5A and 6 showing another embodiment of the present invention. This exemplary cutting head 70 again includes three cutting blades 70a each extending radially outward at even angular intervals.

[0050] Each cutting head 70a includes a first planar region 70b oriented at an obtuse angle  $\delta$  below a plane formed by the body 80 of the cutting head. The first planar region 80b extends radially outward a first distance  $d_1$  from a center 80b of the body 80 and intersects with a first rake face 70d to form a first cutting edge 70g. The first planar region 70b extends from the first rake face 70d at a leading edge of the cutting blade 70a, which is substantially normal to the planar region 70b, to a second rake face 70e at a trailing edge of the cutting blade 70a, which is also substantially normal to the first planar



region 70b. A second planar region 70c is formed at an acute angle  $\theta$  above the first planar region 70b. The second planar region 70c extends radially outward a second distance  $d_2$  from the center 80b of the body 80. A second cutting surface or rake face 70h, substantially normal to the second planar region 70c, is formed at an intersection with an end face 70f, which is also substantially normal to the second planar region 70c. The distance  $x_2$  between the second cutting surface or rake face at the leading edge of the second planar region 70c and a rake face 70i at the trailing edge of the second planar region 70c is less than the distance  $x_1$  between the first rake face 70d at the leading edge of the first planar region 70b and the second rake face 70e at the trailing edge of the first planar region 70b.

[0051] FIG. 9 shows view D corresponding to the arrow in FIG. 8, wherein, a rake face 70d of the cutting blade 70a is oriented at an angle  $\alpha$  with respect to a direction opposite to the rotational direction B of the cutting head 7 in FIG. 4 and with respect to a line L normal to the cylinder bore inner surface 5. The orientation of the rake face 7d in FIG. 5A may also be selected to have the same orientation as the rake face 70d in FIG. 9. At the same time, a rake face 70h adjacent the second planar surface part 70c is oriented at an angle  $\beta$  in the rotational direction B with respect to a line M drawn orthogonal to the surface 5 to be roughened.

[0052] FIG. 10 illustrates a cutting procedure using the cutting head of FIG. 8. The first cutting edge 70g cuts into the surface 5 of the cylindrical body a first machined pattern of peaks and valleys, which is preferably a substantially helical thread-like pattern. The first cutting edge 70g is typically shaped at an angle  $\sigma$  with respect to the first rake face 70d such that each machined valley in the surface 5 is symmetrical, and in a preferred embodiment each valley has a v-shape when viewed in cross section. The second cutting edge 70h then applies stress to the peaks of the first machined pattern, which fractures the peaks and forms a second machined pattern in the surface 5, which also substantially helical. In the second machined pattern the fractured peaks form a patterns of roughened lands separated by grooves, which are the valleys remaining from the first machined pattern.

[0053] The second cutting edge 70h preferably removes the entire cross direction of the peak 17 (vertical direction in FIG. 10 and up out of the paper toward the viewer) to form a fracture surface 19 that is almost the same as that shown in FIG. 7. The end face 70f that is located at the tip of the second planar region 70c then contacts the fracture surface 19 after the peak 17 is removed. Since the rake surface 70h of the projecting part 70c is

oriented at an angle  $\beta$  in the rotational direction B with respect to a line M normal to the surface 5, while the rake surface 70d is oriented at an angle  $\alpha$  in the direction opposite the rotational direction B with respect to a line L normal to the surface 5, the removal of the peak 17 may be more reliably performed compared to a tool design in which the rake surface 70h is oriented in the same direction as the rake surface 70d.

**[0054]** In certain presently preferred embodiments, the trailing edge of the cutting head may also roughen the surface of each land after the peak is fractured and removed, which increases the surface area of the land and may enhance adhesion of the coating to the land. FIG. 11 is a cross-sectional view corresponding to FIG. 10 showing an example of a cutting head 70 useful in practicing this presently preferred embodiment. In this example, an irregularly shaped part with projections and recessions which makes the irregularly shaped fracture surface 19 with projections and recessions is provided on an end face 70fs in the second planar surface 70c of the cutting head 70, which contacts the fracture surface 19 after the peak 17 is removed by the second cutting surface 70h. The roughened surface 70fs creates a finer surface texture on the fracture surfaces 19, which enhances the surface area and would be expected to increase the adhesion of the coating.

**[0055]** FIG. 12 is a block diagram showing an outline of exemplary thermal spraying equipment useful in forming a roughened surface on a cylinder bore inner surface according to another embodiment of the present invention. FIG. 12 illustrates a schematic of the thermal spraying equipment used to form a thermal spray coating after roughening the surface on the cylinder bore inner surface 5 of the cylinder block 1. This exemplary thermal spraying equipment inserts a gas wire thermal spraying gun 31 into the center of a cylinder bore, and a fused ferrous metallic material of a thermal spraying material is sprayed in the form of droplets 33 from a thermal spraying port 31a to form a thermal spray coating 32 on the cylinder bore inner surface 5.

**[0056]** The thermal spraying gun 31 may be fed a supply of melting wire 37 of a ferrous metallic material as the material for thermal spraying from a melting wire feeding machine 35, and further may receive a supply of a fuel gas and oxygen from a fuel gas cylinder 39 which stores fuel such as acetylene, propane, ethylene, and the like; and from an oxygen cylinder 41 which stores oxygen and delivers oxygen gas, through piping 43 and 45 respectively. The melting wire 37 may be fed to the thermal spraying gun 31 from the upper end to the lower side of a melting wire feed hole 47 that vertically penetrates the central part of the gun. In addition, the fuel and oxygen may be supplied to a gas guide channel 51 that is formed by vertically penetrating a cylindrical part 49 located on

the outside of the melting wire feed hole 47. This mixed gas supply of fuel and oxygen may flow out from a lower end opening 51a of the gas guide channel 51 in FIG. 12 and when ignited, forms a combustion flame 53.

[0057] An atomized-air channel 55 may be provided on the outer circumference of the cylindrical body 49, and an accelerated-air channel 61 formed between a cylindrical bulkhead 57 and a cylindrical external wall 59 is provided outside of the atomized-air channel. Atomized-air flowing through the atomized-air channel 55, may be pre-heated by the combustion flame 53, and fed forward (downward in FIG. 12) in order to allow the perimeter part to cool. Atomized-air may also be fed forward to the fused melting wire 37. At or about the same time, accelerated-air flowing through the accelerated-air channel 61 is also fed forward, and feeds the melted melting wire 37 to the cylinder bore inner surface 3 as droplets 33 so that it intersects with the feed direction to form the sprayed coating 32 on the cylinder bore inner surface 5.

[0058] Atomized-air may be supplied to the atomized-air channel 55 from an atomized-air supply source 67 through an air supply pipe 71 with a pressure regulator 69. At or about the same time, accelerated-air is supplied to the accelerated-air channel 61 from an accelerated-air supply source 73 through an air supply pipe 79 with a pressure regulator 75 and a micromist filter 77. The bulkhead 57 between the atomized-air channel 55 and the accelerated-air channel 61 includes of a rotary cylinder part 83 which can be rotated through a bearing 81 of the external wall 59 at the tip of the lower side in FIG. 12. A rotary wing 85 that is located in the accelerated-air channel 61 is provided on the upper outer circumference of this rotary cylinder part-83. When accelerated-air flowing through the accelerated-air channel 61 works on the rotary wing 85, the rotary cylinder part 83 rotates.

[0059] A tip part 87 that rotates integrally with the rotary cylinder part 83 may be fixed on the tip (lower end) 83a of the rotary cylinder part 83. A projecting part 91 with a spout channel 89 that communicates with the accelerated-air channel 61 through the bearing 81 is provided on one part of the peripheral edge of the tip part 87, and the thermal spraying port 31a which spouts out droplets 33 is provided at the tip of the spout channel 89. By rotating the tip part 87 with the thermal spraying port 31a integrally with the rotary cylinder part 83, while moving the thermal spraying gun 31 in the axial direction of the cylinder bore, a sprayed coating 32 is formed on almost the entire area of the cylinder bore inner surface 5.

[0060] Although in each of the embodiments explained above, surface roughening is performed at the internal surface of cylindrical bodies such as with the cylinder bore inner surface 5, another embodiment explained below illustrates increasing the bonding strength of a cylinder liner 103 with a cylinder block 101 by roughening the outer peripheral surface 103a of the cylinder liner 103, that is the outer surface of a cylindrical body, by means of a similar method to the cylinder bore inner surface 5 in each of the embodiments described above. This embodiment may be particularly useful when the cylinder liner 103 is made of, for example, cast iron, and the cylindrical body is cast into a cylinder block 101 that is made of, for example, an aluminum alloy, as shown in FIG. 13.

[0061] FIG. 14A is a top view of the cylinder liner 103 in FIG. 13, and FIG 14B is a plane view of FIG. 14A showing the roughened exterior peripheral surface 103a of the cylinder liner 103 of FIG. 13. The outer peripheral surface 103a of the cylinder liner 103 is cut into a first substantially helical pattern of peaks and valleys using the cutting blade 7a (70a) of the boring bar 9 with the cutting head 7 or 70 as shown in FIG. 2. The peaks 17 of this first substantially helical pattern are fractured by the leading edge 7h (70h) of the projection formed by the second planar surface 7c (projecting part 70c) to form a pattern of grooves interspersed with fracture surfaces 19 as shown in FIG. 7. In this manner, a cylinder liner 103 can be obtained in which the outer peripheral surface 103a is roughened as shown in FIG. 14 (a).

[0062] In another embodiment shown in FIG. 15, the cylindrical cylinder liner 103 with the roughened outer peripheral surface 103a may be cast to mold integrally when the cylinder block 101 is cast with a casting mold. The casting mold includes of a bottom die 105, an upper die 107, right and left side die 109 and 111, front and rear die 113 and 115, and an ejector plate 117 installed in the upper part of the upper die 107. A bore core 107a for forming a cylinder bore 101a of the cylinder block 101 is provided at the side opposite to the bottom die 105 of the upper die 107, and the cylinder block 101 is cast and formed in a state such that the cylinder liner 103 is kept as shown in FIG. 14 on this bore core 107a.

[0063] As shown in FIG. 1 and FIG. 13, the cylinder bore part 3 of cylinder block 101 in which the cylinder liner 103 is cast, can also be surface roughened according to various previously described embodiments of the presently disclosed invention. In addition, since the outer peripheral surface 103a of the cylinder liner 103 may be roughened using the same or a similar method to that used for the cylinder bore inner surface 5 at about the

same time, the joining strength of the cylinder block 101 for the cylinder liner 103 can be increased and a cylinder block 101 of high quality can be obtained.

**[0064]** Various embodiments of the invention have been described. These and other embodiments are within the scope of the following claims.

**CLAIMS:**

1. A surface roughening method, comprising:  
moving a cutting tool having a cutting head along a longitudinal axis of an article, wherein the cutting head comprises a radial cutting blade having a first cutting edge and a second cutting edge; and  
rotating the cutting head about the longitudinal axis of the article such that the first cutting edge of the cutting blade forms a first machined pattern of peaks and valleys on a surface of the article,  
wherein the second cutting edge of the cutting blade removes at least a portion of the peaks in the first machined pattern to form roughened fracture surfaces in a second machined pattern on the surface of the article, and  
wherein the second machined pattern comprises an arrangement of grooves corresponding to the valleys in the first pattern and separated by lands corresponding to the roughened fracture surfaces.
2. The method of claim 1, wherein an entire cross section of each peak in the first pattern is fractured.
3. The method of claim 1, wherein each of the grooves in the second machined pattern is symmetrical.
4. The method of claim 1, wherein each of the grooves in the second machined pattern defines a v-shape.
5. The method of claim 1, wherein a trailing edge of the cutting head roughens the surface of each land.
6. The method of claim 1, wherein the article defines a cylindrical body.

7. The method of claim 6, wherein the first cutting edge cuts an interior surface of the cylindrical body into the first machined pattern comprising a first substantially helical pattern defined by the alternating peaks and valleys, and wherein the second cutting edge creates the roughened fracture surfaces on the interior surface by applying stress on the peaks to fracture at least a portion of the peaks to form the second machined pattern comprising a second substantially helical pattern defined by lands corresponding to the roughened fracture surfaces, separated by grooves corresponding to the valleys.
8. The method of claim 1, wherein the article comprises a nonferrous metal.
9. The method of claim 1, further comprising applying a coating overlaying the first and second machined patterns on the surface of the article.
10. The method of claim 9, wherein applying the coating comprises at least one of chemical vapor deposition, plasma deposition, thermal spray coating, or fluid spray coating.
11. The method of claim 9, wherein the coating comprises an abrasion resistant material.
12. The method of claim 9, wherein the coating comprises at least one of a ceramic material or a ferrous metal.
13. The method of claim 12, wherein the ceramic material comprises one or more of silicon nitride, silicon carbide, aluminum oxide, silicon dioxide, and titanium nitride.
14. The method of claim 12, wherein the ferrous metal comprises one or more of titanium, tungsten, cobalt, nickel, iron, and aluminum.

15. A surface roughening system, comprising:

means for roughening a surface comprising first cutting edge means for cutting a first pattern of peaks and valleys into the surface, and a second cutting edge means for fracturing the peaks;

means for moving the means for roughening in an axial direction relative to a longitudinal axis of the surface; and

means for rotating the means for roughening in a radial direction relative to the surface;

wherein rotating the means for roughening while feeding the means for roughening relative to the surface creates a roughened surface comprising a second pattern, wherein the second patterns comprises a plurality of lands created by fracturing the peaks, each land positioned adjacent to a groove corresponding to a respective one of the valleys in the first pattern.

16. A cutting tool comprising:

a rotary cutting head comprising a body having at least one cutting blade extending radially outward therefrom, wherein the cutting blade comprises a body, a first planar surface and a second planar surface,

wherein the first planar surface is shaped to cut a first pattern of peaks and valleys into a surface of an article, and

wherein the second planar surface is shaped to fracture the peaks in the first pattern to create a second pattern comprising lands corresponding to the fractured peaks, and wherein the fractured peaks are separated by grooves corresponding to the valleys in the first pattern.

17. The cutting tool of claim 16, wherein the first planar surface of the cutting blade extends a first radial distance from a center of the body of the rotary cutting head, and the second planar surface extends a second radial distance from the center of the body of the rotary cutting head, and wherein the first distance is greater than the second distance.

18. The cutting tool of claim 17, wherein the first planar surface of the cutting blade is oriented at an obtuse angle below a plane of the body of the rotary cutting head.



19. The cutting tool of claim 16, wherein the first planar surface comprises a first rake surface substantially normal thereto, and the second planar surface comprises a second rake surface substantially normal thereto, and wherein the first rake surface and the second rake surface are the same surface.
20. The cutting tool of claim 16, wherein the first rake surface and the second rake surface are different surfaces.
21. The cutting tool of claim 16, wherein the second planar surface comprises an end face substantially normal thereto, and wherein the end face is roughened.
22. The cutting tool of claim 16, wherein the first cutting edge is shaped to form a symmetrical groove with a cross sectional v-shape.
23. The cutting tool of claim 16, wherein the rotary cutting head comprises at least one of a metal, a ceramic material, or diamond.
24. The cutting tool of claim 23, wherein the cutting blade comprises at least one metal selected from titanium, tungsten, cobalt, nickel, iron, or aluminum.
25. The cutting tool of claim 23, wherein the cutting blade comprises at least one ceramic material selected from comprises one or more of silicon nitride, silicon carbide, aluminum oxide, silicon dioxide, or titanium nitride.
26. A cylindrical body having a machine roughened surface, wherein the roughened surface comprises a substantially helical pattern of grooves separated by lands corresponding to substantially uniform roughened surface regions, wherein the cross section of the grooves is substantially symmetrical and each groove has a v-shape.
27. The body of claim 26, wherein the machine roughened surface is an interior surface of the cylindrical body.
28. The body of claim 26, wherein the cylindrical body comprises a nonferrous metal.

29. The body of claim 28, further comprising a coating applied to the machine roughened surface.
30. The body of claim 29, wherein the coating comprises an abrasion resistant material.
31. The body of claim 29, wherein the coating comprises at least one of a ceramic material or a ferrous metal.
32. The body of claim 31, wherein the ceramic material comprises one or more of silicon nitride, silicon carbide, aluminum oxide, silicon dioxide, and titanium nitride.
33. The body of claim 31, wherein the ferrous metal comprises one or more of titanium, tungsten, cobalt, nickel, iron, and aluminum.
34. The body of claim 26, wherein the machine roughened surface comprises an inner surface of a cylindrical bore in a cylinder block of an internal combustion engine.
35. The body of claim 34, further comprising a coating applied to the inner surface overlaying the lands and the grooves.
36. The body of claim 35 wherein the coating comprises an abrasion resistant material.
37. The body of claim 35, wherein the coating comprises at least one of a ceramic material or a ferrous metal.
38. The body of claim 37, wherein the ceramic material comprises one or more of silicon nitride, silicon carbide, aluminum oxide, silicon dioxide, and titanium nitride.
39. The body of claim 37, wherein the ferrous metal comprises one or more of titanium, tungsten, cobalt, nickel, iron, and aluminum.


40. The body of claim 26, wherein the machine roughened surface comprises an outer surface of a cylindrical liner inserted within a cylinder bore of a cylinder block of an internal combustion engine.

41. The body of claim 40, wherein the cylindrical liner comprises an outer peripheral surface that comprises the machine roughened surface by forming thereon the pattern of lands and grooves, and joined to an inner surface of the cylinder bore.


**CUTTING TOOLS AND ROUGHENED ARTICLES**  
**USING SURFACE ROUGHENING METHODS**

**ABSTRACT**


The disclosure relates to surface roughening methods in which a cutting tool having a radial cutting blade with first and second cutting edges is fed along a longitudinal axis of an article while rotating the cutting tool about the axis. The first cutting edge forms a first machined pattern of peaks and valleys on a surface of the article, and the second cutting edge removes at least a portion of the peaks to form roughened fracture surfaces in a second machined pattern defining an arrangement of grooves, corresponding to the valleys, separated by lands, corresponding to the roughened fracture surfaces. The disclosure also provides cutting tools useful in practicing the surface roughening methods. The disclosure further describes cylindrical articles having interior or exterior surfaces roughened using the methods. The methods, cutting tools and articles have applications including fabrication of cylinder blocks for internal combustion engines.




**Fig. 1**




**Fig. 2**




**Fig. 3**




**Fig. 4**




**Fig. 5**




**Fig. 5A**




**Fig. 6**




**Fig. 7**



**Fig. 8**




**Fig. 9**




**Fig. 10**




5/7




**Fig. 11**




**Fig. 12**




**Fig. 13**



**Fig. 14A**



**Fig. 14B**

**Fig. 15**